



PRODUCT DATA SHEET	Page: 1 of 2
	US Revision: 2
RD-ELASTODECK QUARTZ	Date: 10/15/2011
	Supersedes: 01/15/2009
	R11

DESCRIPTION OF THE PRODUCT

Water-borne acrylic polymer, high performance, single component coating filled with an aggregate to produce a non-skid surface for the RD Coatings products.

USES: To be used as a non-skid coating for the RD Coatings systems.

FEATURES:

- VOC- 8g/L, single package, water-borne.
- Contains no chromates, lead or strong solvents.
- Impact and erosion resistant.
- Resistant to the effects of long-term weathering, UV light, salt water and most environmental chemicals.
- Thixotropic non-sag properties allowing applications in thick layers up to 20 mils.

SUBSTRATES:

- Concrete
- CMU Block
- Brick
- Steel
- Non-Skid coating over any RD Coatings product

APPLICATION INSTRUCTIONS

PREPARATION OF THE SUBSTRATE: Prepare substrates by pressurized water cleaning using 4,000-5,000 psi pressure equipment equipped with a “zero” oscillating tip. Remove any remaining loose and non-adhering substrate prior to coating. Apply to a clean, dry, sound surface. RD-ELASTODECK QUARTZ may be applied directly to prepared substrate or to surfaces primed or coated with any RD Coatings product.

APPLICATION CONDITIONS: Environmental Conditions (general requirements):

- The minimum air and substrate temperatures; 45°F for 24hours.
- The maximum surface temperature; 130°F.
- The maximum relative humidity: 90%.
- Surface temperature must be at least 5°F above the Dew Point, with no threat of rain for 3hours.

Drying Times Temperature Re-Coat Interval:
60°F (80%RH) 7 Hours
80°F (80%RH) 5 Hours
95°F (80%RH) 3 Hours

Notes: The above figures are for RD-ELASTODECK QUARTZ applied @ 12 wet mils. These figures do not account for airflow; wind speeds of even 5mph will greatly reduce the dry time.

APPLICATION MEANS:

- In most cases this product is applied using a brush or roller.
- It can also be spray applied using a conventional air assisted texture gun.

DILUTION: Can dilute with water to reduce viscosity.



PRODUCT DATA SHEET	Page: 2 of 2
	US Revision: 2
RD-ELASTODECK QUARTZ	Date: 10/15/2011
	Supersedes: 01/15/2009
	R11

CLEANING OF TOOLS: Water

CONSUMPTION: Theoretical Coverage / 4.25 Gallon Container:
• 550 sq. ft. at 6 mils DFT

PARTICULARITIES: Mix before use.

TECHNICAL DATA

FINISH: Flat

COLORS: Light Green / Dark Green

SOLIDS CONTENT: In Weight: 65-67%
In Volume: 58-61%

FLASH POINT: Non-Flammable

DRYING TIME: To Touch: 3-6 hours
To Recoat: 6-24 hours, depending on temperature and humidity.

PACKING: 4.25 Gallon Units

STORAGE STABILITY: 2 years minimum; provided the original container is sealed and has been stored in a controlled environment.

TEST DATA: Available upon request.

SAFETY DATA

The safety data sheet is available on request. (See RD-ELASTODECK MSDS)

This Data is given for information only. Since the manufacturer is not able to check the correct application of the products, they cannot accept any responsibility for it. This technical data sheet replaces all previous editions.